

#### **Grounding & Cleaning**

If the material is used on top of an already properly grounded surface, grounding hardware may not be necessary. Where no properly grounded surface is available, grounding hardware is required to provide a path-to-ground. Rtg compliance verification measurements must be made as outlined in ESD TR53 with a surface resistance meter.

### Limited Lifetime Warranty:

Desco warrants for one year that Statfree® matting products will be fre of defects in materials and workmanship and will guarantee dissipative conductive mat properties for the life of the mat. Damage to matting caused by misuse of any kind, including using inappropriate cleaners not covered by Desco Limited Warranty.



Test Equipment 99 Washington Street Depot Melrose, MA 02176 Phone 781-665-1400 Toll Free 1-800-517-8431

Visit us at www.TestEquipmentDepot.com

## STATFREE T2<sup>™</sup> DISSIPATIVE RUBBER



### Specifications

Standard Document ANSI/ESD S20.20		Meets Requirements of: Worksurface
Electrical Properties Dissipative Surface Layer Rtt Resistance: Rtg Resistance:	Typical Values	Test Procedures/Method
	1 x 10 <sup>6</sup> to < 1 x 10 <sup>9</sup> ohms 1 x 10 <sup>6</sup> to < 1 x 10 <sup>9</sup> ohms	ANSI/ESD S4.1 and ESD TR53 ANSI/ESD S4.1 and ESD TR53
Ground Plane Layer Rtt Resistance:	< 1 x 10 <sup>6</sup> ohms	ANSI/ESD S4.1 and ESD TR53
Physical Properties Construction: Thickness: Color: <sup>2</sup> Embossing: <sup>2</sup> Weight: Hardness:	Dual-layer rubber material <sup>1</sup> 0.060" (1.5mm) Blue (Top), Dark Blue (Top Slight Texture 0.43 lbs./sq. ft. (0.2g/cm2) 65 ± 5 Shore "A", per ASTM	), Dark Grey (Top), Green (Top), Black (Bottom) M-D2240
Other Properties Heat Resistance: Chemical Resistance:		n coming into contact with hot solder and soldering iron by inorganic acids, organic acids, reducing agents, aliph aldehvdes, and amines.
<sup>1</sup> Rubber material isvulcanize <sup>2</sup> Color and texture may vary		
<b>Tolerances:</b> Width ± 0.250" Length ± 0.250" every 1 line Thickness ±10%	Ŭ	first unrolled. In applications where length is critical, allo
	east 4 hours before cutting to s	size. Always using care trim with a sharp knife or razor b
	east 4 hours before cutting to a	

Specifications and procedures subject to change without notice.



# MATERIAL

STATFREE T2<sup>™</sup> DISSIPATIVE, RUBBER, 2-LAYER, 0.060" (1.5mm)

STATFREE T2<sup>™</sup> **DRAWING PM-104**